



**Thai Nair Wu Jin CO., LTD.**

224/50-52 Larnluang Road, Klong Mahanak, Pomprab,

Bangkok 10100, Thailand

T: (+662)281-4707 282-3822

E: info@thaiwujin.com

### Aluminium Brass C68700 : Al-Brass Composition

Al Brass Standard	Alloy Number	CU	PB	FE	ZN	P	AL	AS	Impurities
BS 2871 PART3	CZ110	76.0-79.0	max 0.05	max 0.07	Remainder	max 0.1	1.8-2.3	0.02-0.06	max 0.3
ASTM B111	C68700	76.0-79.0	max 0.07	max 0.06	Remainder	-	1.8-2.5	0.02-0.06	-
DIN 1785	CuZn20 AL2	76.0-79.0	max 0.07	max 0.07	Remainder	-	1.8-2.3	0.02-0.035	max 0.1
JIS H3300	C6870 T	76.0-79.0	max 0.05	max 0.05	Remainder	-	1.8-2.5	0.02-0.06	-